

TRYMER™ 3000

Polyisocyanurate Insulation

TRYMER™ 3000 insulation is a polyurethane modified polyisocyanurate cellular material. The rigid insulation is supplied in the of bunstock for fabrication into sheets, pipe shells, tank and vessel coverings, and other shapes for a variety of thermal insulation applications.

TRYMER™ 3000 insulation features improved dimensional stability over a wider range of temperatures than standard polyurethane insulation. TRYMER™ insulation is not a known nutrient source for mold and mildew.

Applications

TRYMER™ 3000 insulation is used extensively in industrial and commercial applications with moderate density/strength requirements, within the service temperature range of -297°F to +300°F (-183°C to +149°C).

Typical applications for

TRYMER™ 3000 insulation include:

- industrial pipe insulation, including elbows and fittings
- cryogenic system insulation, such as liquefied natural gas (LNG)
- tank and vessel insulation
- core material for architectural and structural panels
- core material for factory-built panelized constructions

ITW can provide general guidelines and recommendations for TRYMER™ 3000 insulation. For additional information, visit www.itwinsulation.com, call 1-800-231-1024 or contact your local ITW representative.

SIZE	
Height:	18" (45.72 cm)
Width:	48" (122 cm)
Length:	36" (91 cm) 96" (244 cm)

Custom lengths are also available. Contact your local ITW representative for details.

PHYSICAL PROPERTIES

TRYMER™ 3000 insulation exhibits the properties and characteristics indicated in Table 1 when tested as represented.

Consultation with local code officials and design engineers/specifiers is recommended before application.

As with all cellular polymers, TRYMER™ 3000 insulation will degrade upon prolonged exposure to sunlight. A covering to block ultraviolet radiation must be used to prevent degradation. Other coverings to protect the insulation from the elements may be required.

ENVIRONMENTAL DATA

TRYMER™ 3000 insulation is specifically formulated to provide excellent thermal insulation properties without the use of chlorofluorocarbon (CFC) or hydrochlorofluorocarbon (HCFC) blowing agents. In compliance with the Montreal Protocol and the Clean Air Act, TRYMER™ 3000 insulation is manufactured with hydrocarbon blowing agents, which have no ozone depletion potential.

SAFETY CONSIDERATIONS

TRYMER™ 3000 insulation requires care in handling. All persons working with this material must know and follow the proper

handling procedures. The current Material Safety Data Sheet (MSDS) and General Handling Recommendations for TRYMER™ contains information on the safe handling, storage and use of this material. For copies of these documents, visit the literature library at www.itwinsulation.com, call 1-800-231-1024 or contact your local ITW representative.

Installation

TRYMER™ 3000 insulation is specifically formulated for easy fabrication into many shapes, such as pipe coverings, valve and fitting covers, and others to meet specific design needs.

Because of the critical technical design aspects in many applications, ITW recommends contacting qualified designers to specify the total system. For more specific instructions, contact a local ITW representative or access the literature library at www.itwinsulation.com.

Availability

TRYMER™ 3000 insulation is distributed through ITW's extensive Authorized Fabricator Network. For more information, call: 1-800-231-1024

Technical Services

ITW can provide technical information to help address questions when using TRYMER™ 3000 insulation. Technical personnel are available at: 1-800-231-1024

TABLE 1

Physical Properties of TRYMER™ 3000 Polyisocyanurate Insulation					
Property ⁽¹⁾ and Test Method ⁽²⁾		Value	Property ⁽¹⁾ and Test Method ⁽²⁾		Value
Density ⁽³⁾ , ASTM D1622, lb/ft ³ (kg/m ³)		3 (48.0)	Water Absorption, ASTM C272, 24-hr immersion, % by volume		<0.7
Compressive Strength ⁽³⁾ , ASTM D1621, lb/in ² (kPa)			Water Vapor Permeability, ASTM E96, perm-inch (ng/Pa•s•m)		3 (4.6)
Parallel to rise – thickness		65 (450)	Dimensional Stability ^{(3),(5)} , ASTM D2126		
Perpendicular to rise – width		45 (310)	At -40°F (-40°C), 7 days		
Perpendicular to rise – length		55 (380)	Length, % change		-0.2
Compressive Modulus, ASTM D1621, lb/in ² (kPa)			Volume, % change		-0.2
Parallel to rise – thickness		1,200 (8,270)	At -10°F (-23°C), 7 days		
Perpendicular to rise – width		800 (5,500)	Length, % change		0.2
Perpendicular to rise – length		1,200 (8,270)	Volume, % change		0.2
Shear Strength, ASTM C273, lb/in ² (kPa)			At 158°F (70°C), 7 days		
Parallel and perpendicular, avg		25 (172)	Length, % change		1.5
Shear Modulus, ASTM C273, lb/in ² (kPa)			Volume, % change		3.0
Parallel and perpendicular, avg		375 (2,600)	At 158°F (70°C)/97% R.H., 7 days		
Tensile Strength, ASTM D1623, lb/in ² (kPa)			Length, % change		1.0
Parallel to rise – thickness		40 (275)	Volume, % change		2.4
Flexural Strength, ASTM C203, lb/in ² (kPa)			At 300°F (149°C), 7 days		
Parallel to rise		60 (413)	Length, % change		1.4
Flexural Modulus, ASTM C203, lb/in ² (kPa)			Volume, % change		2.0
Parallel to rise		1,230 (8,480)	Service Temperature ⁽⁶⁾ , °F(°C)		-297 to +300 (-183 to +149)
k-factor, ASTM C518, Btu•in/hr•ft ² •°F (W/m•°C)			Surface Burning Characteristics ⁽⁷⁾ , ASTM E84		25/450 up to 6" (15 cm) thickness
Aged 180 days @ 75°F (24°C)		0.19 (0.027)	Flame Spread/Smoke Developed (FS/SD)		
R-Value ⁽⁴⁾ /in., ASTM C518, hr•ft ² •°F/Btu (m ² •°C/W)			Color		Tan
Aged 180 days @ 75°F (24°C)		5.3 (0.93)			
Closed Cell Content, ASTM D2856, %, min.		95			

- (1) All properties are measured at 74° (23°C), unless otherwise indicated.
- (2) Unless otherwise indicated, data shown are typical values obtained from representative production samples. This data may be used as a guide for design purposes, but should not be construed as specifications. For property ranges and specifications, consult your ITW representative.
- (3) Average value through insulation cross section.
- (4) R means resistance to heat flow. The higher the R-value, the greater the insulating power.
- (5) Frequent and severe thermal cycling can produce dimensional changes significantly greater than those stated here. Special design consideration must be made in systems that cycle frequently.
- (6) Above 300°F (149°C), discoloration and charring will occur, resulting in an increased k-factor in the discolored area.
- (7) This numerical flame spread data is not intended to reflect hazards presented by this or any other material under actual fire conditions.

- For Technical Information: 1-800-231-1024
- For Sales Information: 1-800-231-1024
- ITW Insulation Systems
- 1370 East 40th Street, Building 7, Suite 1, Houston, TX 77022-4104
- www.itwinsulation.com

NOTICE: No freedom from any patent owned by ITW or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. ITW Insulation Systems assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

COMBUSTIBLE: Protect from high heat sources. Local building codes may require a protective or thermal barrier. For more information, consult MSDS, call ITW at 1-800-231-1024 or contact your local building inspector.

Building and/or construction practices unrelated to insulation could greatly affect moisture and the potential for mold formation. No material supplier including ITW can give assurance that mold will not develop in any specific system.